

FLOWPATCH® FLOWPATCH® COLOURED

Quick setting, pourable repairs for heavily trafficked floors



AREAS OF USE

- Ideal for filling deep holes before screeding with Watco Flowtop®

FEATURES

- Just add water, mix and pour
- Can be applied to damp (not wet) concrete
- Sets at low temperatures (down to 5°C)
- Can be applied at any depth between 5mm -100mm
- Slip resistant finish
- Fibre reinforced

DESCRIPTION

Watco Flowpatch® is an easy to mix pourable material for quick repairs to level concrete, inside or outside. Watco Flowpatch® is very strong and hardens quickly: it will accept heavy traffic including forklifts only 2 hours after application.

For repairs to ramps, steps and for reforming edges, we recommend Watco Concrex®. For resurfacing or levelling larger areas of rough or tamped concrete please use Watco Flowtop®.

Watco Flowpatch® will resist oils and grease. If greater chemical resistance is required, please use Watco Concrex®.

It can be applied at any depth between 5mm -100mm and repairs can be feather edged in light traffic areas. When mixed, Watco Flowpatch® will be pourable so is not suitable for repairs to sloping floors or exposed edges.

After curing, Watco Flowpatch® can be painted with any suitable Watco floor paint. If the floor being repaired is very rough, you may wish to screed the whole floor with Watco Flowtop® for a smooth flat surface before painting.

The surface is inherently anti slip in dry conditions. Overcoating with Watco Safety Grip® is recommended if positive anti slip is required in very wet or oily conditions. Watco Safety Coat is available where a general level of slip resistance is required. Watco Flowpatch® Typical Compressive Strength at 20°C: 1 day: >20N/mm², 7 days: >35N/mm², 28 days: >45N/mm².

SPECIFICATION

Composition	Fibre reinforced, cement based powder.
Number of Components	1
Usage Interior/ Exterior	Interior & exterior.
Application Tools	Steel float or trowel.
Suitable For	Concrete, sand & cement.
Pack Size	25kg
Coverage	Approximately 0.5m ² at 25mm thick
Curing	Watco Flowpatch® will accept foot traffic in 30-60 minutes and forklift traffic in approximately 2 hours at ambient temperatures. Temperatures below 10°C will delay the curing process. As a guide, allow 24 hours when applied at 5°C. Do not apply at temperatures below 0°C. For repairs at low temperatures refer to Watco Concrex® Cold Set.

Pot Life	Approximately 5 to 10 minutes at 20°C, so do not mix at one time more than you can use within a few minutes.
Cleaning Tools	Remove excess with a cloth or scraper and wash with water before the product sets.
Shelf Life	12 months in unopened containers.
Storage	Store in dry conditions. Do not allow to freeze.
Safety.	All product labels provide general safety information. Material Safety Data Sheets are available.

COLOURS



Samples are available on request.

While great care is taken with the colour samples shown, no guarantee can be given that they represent exactly the colours offered.

PREPARATION & APPLICATION

SURFACE PREPARATION

The substrate should be clean and free from oil or contaminants. Any loose material should be removed from the surface. If possible wire brush the surface. Edges of the repair should be cut to depth to avoid feather-edging in heavy wear areas. Watco Flowpatch can be applied to damp (not wet) concrete.

MIXING

Remove the bag of powder from the plastic bucket and use the empty bucket or other suitable container for mixing. If using Flowpatch Coloured add the pigmented powder at this point, at a ratio of 24g per 1kg of Flowpatch powder (600g bag per 25kg). To achieve a pourable mix, add 3 parts of powder to one part of water (by volume).

Due to the short working life of the mixed product, we recommend you carry out the mixing near to the repair, not near to the water source. It's also useful to have a bucket of water nearby, so you can quickly immerse and clean the tools after use.

Put the water into the empty bucket or container and gradually add the powder stirring constantly to achieve a pourable slurry. For small quantities mix by hand using a flat bladed tool such as a spatula, and for larger quantities use a mixer fitted into a slow speed electric drill (Watco Flowtop mixer is ideal). Do not add excessive water or drying time will be extended and the performance may be impaired.

As the mixture hardens quickly, pour the Flowpatch into the hole to be repaired immediately.

We do not recommend re-stirring as this could potentially weaken the final repair. Do not mix more than you can use within a few minutes (5-10 minutes at 20°C).

The remaining powder can be stored for future use.

APPLICATION

When a smooth consistency is achieved, simply pour Watco Flowpatch in to the hole. If the product has been properly mixed it will self level and will need minimal trowelling. Watco Flowpatch can be applied in any depth between 5mm and 100mm. Repairs in lightly trafficked areas can be feather edged, but thin edges are not recommended for medium or heavily trafficked repairs.

SAFETY

Material Safety Data Sheets are available.



WATCO.CO.UK

Watco UK Limited, Eastgate Court, 195-205 High Street, Guildford, Surrey, GU1 3AW, UK Tel: 01483 418 418 Fax: 01483 428 888 www.watco.co.uk E-mail: sales@watco.co.uk