

ASPHALT CRACK FILLER



AREAS OF USE

- Car parks
- Walkways
- School playgrounds
- Private car parks

FEATURES

- Flexible to allow for expansion and movement
- Ideal for cracks up to 3mm
- Cracks 3mm - 25mm can be filled by mixing Watco Asphalt Crack Filler with Watco Sand Additive
- Long lasting protection against ingress of water
- Can be overcoated with Watco Asphalt Paint, Watco Black Top or Watco Asphalt Restorer if required
- Excellent adhesion

Watco Asphalt Crack Filler is a polymer modified flexible crack filler for asphalt, tarmac and all bituminous surfaces. Unsightly cracks in asphalt can lead to water ingress, erosion and accelerated deterioration of the surface. This rubberised bitumen based product makes crack repairs easy. Simply decant the liquid into a spouted can (e.g. a watering can) and pour into the crack.

SPECIFICATION

Composition	Rubberised black bitumen emulsion.	Drying Time	Approximately 2 - 4 hours should be allowed for cracks up to 3mm and 6 - 10 hours for cracks up to 25mm.
Number of Components	1	Cleaning Tools	Use water and detergent if the product has not dried. Once dried, use white spirit.
Usage Interior/Exterior	Exterior & interior.	Shelf Life	12 months in unopened container.
Application Tools	Spouted can.	Storage	Protect from frost and direct sunlight. Do not allow to freeze.
Suitable For	Asphalt, tarmac.	Principle Limitations	This product is designed for use on bitumen based surfaces. It could soften surfaces which contain coal tar. If in doubt, apply a test area and check after 24 hours that no softening has occurred.
Pack Size	5L	Please contact us regarding applications not described here.	
Coverage	5 litres should generally be sufficient for 100m of 5mm wide, 5mm deep crack.		

PREPARATION & APPLICATION

SURFACE PREPARATION

Sweep or scrape out loose debris from the crack.

MIXING

Stir well before use.

APPLICATION

Do not use in wet or cold (below 5°C) conditions. Damp or cold weather will delay the drying time. The crack should be reasonably dry, although a little dampness may be tolerated.

Cracks up to 3mm wide – Pour the Watco Asphalt Crack Filler into the cracks using a spouted can (available from Watco). Alternatively a watering can may be used.

Brush out to a thin film any surplus liquid which overflows the edges of the crack.

Once the Watco Asphalt Crack Filler has dried, dust with very fine sand or cement to remove any residual tack.

Cracks 3mm - 25mm wide – Prime the sides of the crack with a brush coat of Watco Asphalt Crack Filler. Mix Watco Asphalt Crack Filler with damp sand (Watco Sand Additive is available) to produce a slightly stiff mortar. Trowel into the crack and smooth off. Once the mortar is dry, dust with very fine sand or cement to remove any residual tack.

SAFETY

All product labels provide general safety information. Material Safety Data Sheets are available. Food products must be removed from the area during application and cure.



WATCO.CO.UK

Watco UK Limited, Eastgate Court, 195-205 High Street, Guildford, Surrey, GU1 3AW, UK Tel: 01483 418 418 Fax: 01483 428 888 www.watco.co.uk E-mail: sales@watco.co.uk