



KÖSTER FS Primer 2C

Technical Data Sheet / Prod. code J 139 200

Issued: 2015-02-20

Two component bonding agent for KÖSTER Joint Sealant FS-V and FS-H for dry and moist substrates

Features

KÖSTER FS Primer 2C is a fast curing, transparent, solvent free two component bonding agent. It is used as a primer for the subsequent application of KÖSTER Joint Sealant FS-H and FS-V.

Technical Data

Viscosity	low viscous
Specific gravity	approx. 1.1 g / cm ³ (+ 20 °C)
Pot life	approx. 20 min. (+ 20 °C)
Installation temperature	+ 5 °C - + 30 °C
Next layer	after 30 - 180 minutes

Safety

Wear solvent resistant gloves and goggles when working with the material. Only work in well ventilated areas.

Related products

KÖSTER Joint Sealant FS-V	Prod. code J 231 004
KÖSTER Joint Sealant FS-H	Prod. code J 232 004
KÖSTER KD System	Prod. code W 219 001
KÖSTER Universal Cleaner	Prod. code X 910 010

Fields of Application

KÖSTER FS Primer 2K is a bonding agent for polysulfide joint sealants.

Substrate

The substrate can be dry or pore saturated, however there may be no water film visible on the surface. The substrate must be free of silicones, loose particles, oil, and grease.

For cleaning substrates, we recommend the use of dirt and grease dissolving water or solvent based cleaning agents. If necessary hot steam clean, grind lightly, or roughen by sandblasting.

Application

Mix the components intensively until a homogenous consistency is reached. KÖSTER FS Primer 2K is applied evenly with a brush in a thin layer.

After a minimum curing time of approx. 30 min KÖSTER Joint Sealant FS-H or FS-V is applied. Apply the KÖSTER Joint Sealant as soon as possible, as absolute care must be taken that no other film, dust, or soiling contaminates the primed surface before application. Completely empty the material from the mixing vessel.

Consumption

Approx. 10 - 20 g/m
or approx. 20 g / meter of joint. The consumption varies depending in the roughness and porosity of the substrate and the width of the joint flanks.

Cleaning

Clean tools immediately after use with KÖSTER Universal Cleaner.

Packaging

J 139 200 200 g combi package

Storage

Store the material between + 10 °C and + 25 °C. In originally sealed containers the material can be stored for approximately 6 months.

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.