



Fastfill WP

Rapid Setting Water Plugging Mortar

Product Overview

Rapid setting cementitious plugging and sealing compound.

Description

FASTFILL WP is a single component, polymer modified, fibre reinforced, Portland cement-based plugging and sealing compound. When mixed with water, it exhibits unique hydraulic properties to produce a rapid setting mortar. It is ideally suited for sealing in and around pipework and for forming fillets in tanking situations.

Uses

For arresting water seepage and infiltration under pressure through cracks, joints, and voids in concrete and masonry. Can also be used for rapid sealing and jointing in and around pipework on water retaining structures.

Advantages

- Pre-packaged material requiring mixing with clean water.
- Low shrinkage and high bond strength ensure monolithic performance and a watertight seal.
- Sets in 2 minutes at 20°C., yielding a durable, high strength mortar.
- Physical properties of cured materials similar to base concrete.
- Polymer modified to prevent wash out and enhance adhesion.
- Non-toxic when cured.
- No more hazardous to handle than ordinary Portland cement.

Application Instructions

Preparation

Mechanically remove all damaged concrete and masonry back to a sound core. Joints and cracks should be dovetail cut or square cut to a minimum depth and width of 20mm. On cutting back, feather edges and V-cuts must be avoided. The perimeter of the area should be broken to a depth of 10mm preferably using a power chisel.

The areas to be treated must be free from all unsound material, i.e. dust, oil, grease, corrosion by-products and organic growth. Smooth surfaces should be roughened, and all loose material and surface laitance removed using high pressure water techniques.

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated without standing water.

Mixing

FASTFILL WP should be mixed by hand in a clean plastic or rubber bowl. Ideally no more than 0.5kg should be mixed at a time using an initial mix ratio by volume of 1 part of water to 3-4 parts of **FASTFILL WP**. Adjust the mix ratio as necessary to give a putty like consistency. Mixing time must not exceed 2 minutes.

Placing

The mixed material should be formed into a ball shape in a gloved hand until slight stiffening occurs. **FASTFILL WP** is then be forced into the void with a minimum of working and held in place firmly for 1-2 minutes until setting occurs.

When sealing joints in pipework or forming a fillet at a wall/floor angle, a steel float or coving trowel may be used to produce the desired finish.

Curing

Once **FASTFILL WP** has been placed and stiffened, the surface should be kept in a damp condition for a minimum of 15 minutes to aid curing.

Cleaning and Storage

- All tools should be cleaned with water immediately.
- Materials can be stored in sealed buckets for 12 months in dry, frost free conditions at 20°C.

Packaging

- **FASTFILL WP** is supplied in 8kg plastic buckets.

Yield and Coverage

- 4.25 litres of mortar per 8kg.
- 8kg covers 0.212m² at 20mm thickness.

Health and Safety

- Safety Data Sheets are available on request.



Application Top Tips

1. Experiment with water contents to achieve different setting times before progressing.
2. Use warm water to accelerate setting further and in cold conditions.
3. Half of a tennis ball or an old hard hat is an ideal mixing vessel.

The information herein is correct to the best of our knowledge, but it does not necessarily refer to the particular requirements of the customer. If the customer has any particular requirements it should make them known in writing to Flexcrete Technologies Limited, and obtain further advice accordingly.

Technical Data

Property	Typical Result
Compressive Strength Development (EN 12190)	1 hour: 4 MPa 1 day: 11 MPa 2 hours: 5 MPa 7 days: 19 MPa 4 hours: 8 MPa 28 days: 26 MPa
Mixed Density	2150kg/m ³
Mixed Colour	Concrete grey
Min Application Thickness	20mm
Final Setting Time	2-3 minutes at 20°C.

The properties given above are obtained from laboratory tests: results obtained from on-site testing may vary according to site conditions.

