

Fosroc® Proofex Total

constructive solutions

High performance, totally gas-resistant, reinforced membrane

Uses

Reinforced gas membrane - designed to protect buildings and their occupants from the effects of methane, radon, carbon dioxide and hydrocarbon vapours, when not in direct contact.

Damp-proof membrane - Proofex Total also acts like conventional ground membranes, as a damp-proof membrane to help protect the building against the ingress of moisture from the ground.

Advantages

- 5-layer product design for maximum gas protection.
- Polyester reinforcing grid for puncture resistance during application.
- Loose-laid system for ease of application.
- Can be used on ground-bearing concrete floors or on suspended concrete or beam and block floors.
- Can be used to form a cavity tray, eradicating the need for a separate product.

Description

Proofex Total is a grey/silver, 5-layer, reinforced, ground gas resistant membrane comprising an aluminium foil layer and a polyester reinforcing grid sandwiched between three layers of polyolefins.

Standard compliances

Independently certified performance, BBA certificate (No. 17/5400).

BRE Digest 211 Radon : Guidance on protective measures for new buildings.

BRE Digest 212: Construction of new buildings on gas contaminated land.

CIRIA 665 - CS 2 & 3-6

BS8485:2015 Table 7 compliant

NHBC - AMBER 1& 2 & RED

Properties

Membrane thickness	0.4 mm
Weight	0.37kg/m ²
Roll weight (2m x 50m)	37 kg
Methane permeability (ISO 15105-1)	<0.1 ml/m ² /day/tm
Colour	Grey / Silver

CE	
Fosroc Ltd Drayton Manor Business Park, Coleshill Road, Tamworth, B78 3XN, UK 13 DOP: UK9-151 0836-CPR-17/F395	
Fosroc® Proofex Total	
EN 13967: Flexible Sheets for Waterproofing: TypeA/ System 2+	
Tensile strength Control - MD /CD	MD: 452 N/50mm CD: 380 N/50mm
Tensile strength Heat Aged - MD /CD	MD: 442 N/50mm CD: 386 N/50mm
Nail Tear Control - MD/ CD	MD: 315 N CD: 331 N
Nail Tear Heat Aged - MD/ CD	MD: 280 N CD: 300 N
Durability of watertightness against ageing	Pass
Durability of watertightness against chemicals	Pass
Joint Strength - Control	118 N/50mm
Joint Strength - Heat Aged	133 N/50mm
Water vapour permeability	<0.03 g/m ² /24h

Application instructions

Preparation

Underslab ground membranes

The hard-core bed should be blinded with soft sand and consolidated to provide a smooth bed free of sharp projections.

Overslab ground membranes

The top surface of the concrete slab should be free from ridges, undulations and sharp projections. If this is not the case a suitable geotextile may be necessary to reduce the risk of puncturing the membrane.



Fosroc® Proofex Total

Laying

The membrane should be laid neatly and tucked well into angles to prevent bridging, with the black surface facing upwards. At corners in upstands folded welts should be formed.

Lapping and jointing

Rolls of Proofex Total should be lapped by a minimum of 150mm and sealed with a continuous strip of Proofex Total Tape. Ensure that the membrane is clean and dry at the time of jointing. Following validation by a specialist engineer, for increased robustness the edge of the upper sheet may be overbanded with Proofex Total Flashing Strip.

Proofex Total can also be heat welded by a specialist installer.

Protection

Protect the completed membrane adequately to prevent puncturing using a geotextile (300g/m² minimum weight) or Proofex Protection Board. Alternatively, the overlying construction, such as insulation, can be installed prior to pouring of concrete. If used in an overslab situation, unbonded screeds should be at least 50mm thick and laid as soon as possible after completing the membrane to reduce the risk of puncture.

Penetrations

Where possible services should be routed such that they do not pass through the membrane, thus reducing the number of penetrations.

Where penetrations are required, Proofex Top Hats are recommended and these should be stuck to membrane using Proofex Total Tape and sealed to pipe with Nitoseal MS60.

Inspection and Repair

Proofex Total is extremely robust and will resist puncture during and after installation providing adequate care is taken to protect the membrane directly after installation. The membrane should be inspected prior to pouring a ground slab or screed and, should any holes or tears be found, these should be repaired using patches of Proofex Total taped in place using Proofex Total Tape with at least a 150mm lap beyond the extremity of the puncture, or Proofex Total Flashing Strip.

The membrane installation should be subject to third-party independent validation in accordance with BS 8485 : 2015.

Ancillary products

Proofex Total Tape

Double-sided butyl tape for sealing of side and end laps and for use in detailing work.

Proofex Top Hats

MDPE sheathing, which encapsulates an aluminium foil layer.

Proofex Total Flashing Strip

Foil tape used for sealing around column penetrations and for repairs/patching of membranes damaged during installation.

Estimating

Proofex Total

Roll width:	2m
Roll length:	50m

Proofex Total Tape

Tape width:	30mm
Tape length:	30m
Tape thickness:	1.5mm

Proofex Total Flashing Strip

Length	10m
Width	300mm
Thickness	1.5mm

Storage

Store in original unopened packaging, in cool dry conditions, away from direct sunlight.

Precautions

Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fosroc and Proofex are trademarks of Fosroc International Limited



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. All Fosroc datasheets are updated on a regular basis. It is the user's responsibility to obtain the latest version.

Fosroc Limited

Drayton Manor Business Park
Coleshill Road, Tamworth,
Staffordshire B78 3XN. UK

www.fosroc.com

telephone:
+44 (0) 1827 262222

fax:
+44 (0) 1827 262444

email:
enquiryuk@fosroc.com

