

Description

rbs Greencure Super is a spray on temporary membrane to retain moisture in freshly placed concrete. It is formulated to prevent evaporation of the gauging water and provides an efficient method for curing concrete. Gives reduced shrinkage and cracking and creates a more durable, hard wearing surface.

Advantages

- High efficiency (90%) spray concrete curing membrane.
- Retains moisture in freshly placed concrete.
- Spray on temporary membrane.
- Reduces surface shrinkage and cracking by controlling moisture.
- Provides a strengthened concrete.
- Dustproofs.
- Non toxic and non flammable.
- No need for damp hessian or polythene.

Directions For Use

- Always stir or shake rbs Greencure Super before use. Apply using a fine spray on-to newly placed concrete. The surface should be free from surface water.
- Coverage rate—4-6m² per litre. All equipment should be cleaned with water.
- Within 28 days the film formed will begin to degrade. Rate of degradation depends on initial membrane thickness and the degree of exposure to UV light.
- rbs Greencure Super does not fall within the scope of BS7542:1992 but has approx a 90% curing efficiency.

Packaging

rbs Greencure Super is available in 20 & 200 Litre containers.

The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use

Storage

rbs Greencure Super should be stored under dry, frost-free conditions away from direct sunlight, under such conditions the shelf life is at least twelve months, if unopened. Once opened replace lid immediately after use and use within 2 weeks.

Technical Data

Appearance	White liquid
Curing Efficiency	>90% at 6m ² per litre
Specific Gravity @ 15.6°C	1.01 (approx)
Flash Point (PMCC)	>100%
Drying Time @ 20°C	Tack free - 2 to 4 hours Hard dry - 18 to 24 hours
Shelf Life (sealed container)	12 months minimum
Compliance	ASTM C-309, Type 1, Class A&B

Important Note

Whilst all reasonable care is taken in compiling technical data on the Company's products, all recommendations or suggestions regarding the use of such products are made without guarantee, since the conditions of use are beyond the control of the Company.

It is the responsibility of the customer to satisfy themselves that each product is fit for the purpose for which they intend to use it. Ensure that the actual conditions of use are suitable, and that in the light of our continual research and development programme, the information relating to each product has not been superseded.

Resapol Ltd

Unit D4, Moss Industrial Estate, Walter Leigh Way,
Leigh, Lancashire WN7 3PT

T 0800 083 1942 E sales@resapol.com

www.resapol.com

Resapol 
Foundation

Giving back with every pack

For more information on the Resapol Foundation, please visit our website at www.resapol.com.