

301 INDUSTRIAL FLOOR PAINT

QUICK DRYING FLOOR PAINT FOR MASONRY, WOOD, CEMENT, CONCRETE AND OTHER SURFACES

DESCRIPTION

301 Industrial Floor Paint is a single pack, easy to use floor paint which dries to a semi-gloss finish and is available in 8 colours. It is easy to use, versatile and economical.

No primer is required for concrete (just dilute 1st coat with 10% white spirit). Other substrates require a suitable primer before application.

ADVANTAGES

- Ready mixed
- Semi-gloss finish
- Available in 8 colours
- Touch dry in just 2 hours @ 20 °C
- No primer required for concrete (just dilute 1st coat with 10% white spirit)
- Application by brush or roller

RECOMMENDED USES

- Ideal for use on masonry, wood, cement, concrete and many other surfaces

TYPICAL PROPERTIES

Specific Gravity:	1.08 to 1.36 @ 20 °C
Volume Solids:	51-60%
Wet Film Thickness:	75 microns
Dry Film Thickness:	40 - 45 microns
Typical Viscosity:	3.5 Poise @ 25 °C
Flash Point:	Above 32°C (closed cup)
V.O.C.	391g/litre*

** VOC's (Volatile Organic Compounds) contribute to atmospheric pollution*

COLOUR RANGE

- White
- Black
- Tile Red
- Steel Blue
- Light Grey
- Flint Grey
- Forest Green
- Yellow

PACK SIZES

- 5 Litre

EXPECTED SPREADING RATE

- 13-15m² per litre @ 40 microns Dry Film Thickness

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

SURFACE PREPARATION

All surfaces should be clean, dry, sound and free from contaminants.

Concrete - power floated, granolithic and smooth surfaces should be roughened first to provide a good "key" for the paint. This can be done mechanically by abrading or blasting, or chemically using Acid Etch. These processes will have the advantage in addition to preparing the surface of also removing dirt and laitance.

New concrete must be allowed to cure thoroughly which can take up to 3 months. Other surfaces must be prepared and primed with the suitable primer for that substrate.

Existing painted surfaces - Surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose and flaking material and treat bare areas as new substrate and prepare accordingly.

MIXING

Mix well before use.

PRECEDING COAT

- 10% thinned 301 Industrial Floor paint on concrete
- Suitable metal or wood primer

APPLICATION CONDITIONS

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

APPLICATION DETAILS

Application restrictions:	N/A
Method:	Brush or Roller
Thinner:	White Spirit Max 10%
(Max vol):	(10%)
Nozzle size:	N/A
Nozzle Pressure:	N/A
Cleaning Solvent:	White Spirit
Recoat Interval:	Minimum 16hrs/Overnight dry

SUBSEQUENT COAT

- 301 Industrial Floor Paint

CURING

- Touch Dry: 2 hours @ 20°C
- Hard Dry: 12 Hours @ 20°C
- Full Hardness: 5 to 7 Days @ 20°C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME

Minimum 16 hours / Overnight dry

STORAGE & SHELF LIFE

- Store only in the original container
- Keep container tightly closed and upright, in a cool, well ventilated place
- See section 7.2 of the [Safety Data Sheet](#) for further information

HEALTH & SAFETY

Please refer to [Material Safety Data Sheet](#) for information.

301 Industrial Floor Paint shall be applied strictly in accordance with the manufacturer's instructions.

For specific advice regarding any aspect of this product, please consult our Technical Department.

The information provided in this Product Data Sheet is intended for general guidance only and is given in good faith based on Rawlins Paints Limited current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this data sheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the Product Data Sheet for the product concerned. All materials are supplied in accordance with our standard terms and conditions of sale (available upon request).

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Rawlins Paints Limited or its agents is based on the information supplied by the purchaser. Rawlins Paints Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.