

PRODUCT DATA SHEET

SikaBond®-5500 S

SOLVENT BASED RIGID ADHESIVE FOR WOOD BLOCK & ENGINEERED WOOD FLOORING

PRODUCT DESCRIPTION

SikaBond®-5500 S is a solvent based rigid adhesive for bonding wood block parquet and engineered boards onto porous substrates. High strength bond, suitable for use with underfloor heating.

USES

For full surface bonding of:

- Traditional parquet blocks and mosaic parquet, industrial parquet and end grained wood paving on cement, anhydrite, and poured asphalt sub-floors
- Can be used over underfloor heating installations
- Especially suited to wood block refurbishment projects where bitumen adhesive residues are present

CHARACTERISTICS / ADVANTAGES

- 1-part, ready to use
- High strength rigid bond
- Very good spreadability
- Excellent adhesion to all types of wood
- Adhesive can be sanded

PRODUCT INFORMATION

| | |
|---------------------|---|
| Chemical Base | 1 part synthetic resin combination |
| Packaging | 16kg metal pails |
| Colour | Beige |
| Shelf Life | 12 months if stored as outlined, in undamaged original sealed container. |
| Storage Conditions | Store in dry conditions, and protect from direct sunlight, at temperatures not lower than +5 or higher than +25°C |
| Density | 1.53 - 1.58 kg/l |
| Service Temperature | up to 35°C |

APPLICATION INFORMATION

| | |
|-----------------------------------|--|
| Consumption | For full surface bonding only. Ensure that the contact faces of the wood elements are fully wetted with adhesive. 0.95 – 1.25 kg/m ² depending upon size of notched trowel used and subfloor surface profile. For the bonding of long or wide boards or in case of uneven substrates it could be necessary to use a notched trowel with bigger notches (avoid hollow sections). |
| Sag Flow | Consistency: Spreads easily, trowel marks stable. |
| Ambient Air Temperature | Room temperature above +10°C, ideally 15°C. Relative air humidity < 75%. For ambient temperatures the standard construction rules are relevant. |
| Relative Air Humidity | Between 40% and 75% |
| Substrate Temperature | During laying and until SikaBond®-5500 S has fully cured substrate temperature must be > + 10°C and in the case of underfloor heating < + 20°C. For substrate temperatures the standard construction rules are relevant |
| Substrate Moisture Content | Maximum substrate moisture content : <ul style="list-style-type: none"> ▪ 2.5% CM (carbide meter) for cement screed (ca. 4% Tramex / Gravimetric weight percent) ▪ 0.5% CM for anhydrite screed ▪ 3 - 12% CM for magnesia flooring (proportion of organic parts) Maximum substrate moisture content in case of underfloor heating: <ul style="list-style-type: none"> ▪ 1.8% CM for cement screed (ca. 3% Tramex / Gravimetric weight percent) ▪ 0.3% CM for anhydrite screed ▪ 3 - 12% CM for magnesia flooring (proportion of organic parts) For moisture content and quality of substrates the guidelines of the wood floor manufacturer as well as standard construction rules must be observed. Please Note: Most wood floor manufacturers state a maximum substrate moisture content of 2% CM (ca.2.5% Tramex). |
| Curing Rate | Floor may be walked on / sanded and finished approximately 48 - 72 hours after installation (depending on climatic conditions, absorbency of sub-floor and adhesive layer thickness). |
| Skin Time / Laying Time | ~ 10 - 20 minutes (+23°C / 50% r.h.) |

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Substrate Quality: Clean and dry, homogeneous, even, free from grease, dust and loose particles. Paint, cement laitance and other poorly adhering particles must be removed. Standard construction rules must be observed.

Substrate Preparation:

Concrete / cement screed: Must be clean, dry, contaminant free and thoroughly cleaned with industrial vacuum cleaner.

Anhydrite screed / Anhydrite flowable screed: Must be ground and thoroughly cleaned with industrial vacuum cleaner.

Underfloor Heating: After thorough preparation and commissioning of the heating system, substrates with high moisture content should be primed using a mixture of 1 part SikaBond®-5500 S to 1 part Everbuild Stick 2 Contact Thinner and Cleaner (by volume).

Roller apply and allow to cure.

Unknown substrates: Please contact our Technical Department.

SikaBond®-5500 S can be used without priming on cement floors, poured asphalt and wooden floor panels providing they are dust free and permanently dry.

Mastic asphalt should be sanded and vacuumed.

APPLICATION METHOD / TOOLS

Full Surface Bonding. SikaBond®-5500 S is only suitable for full surface bonding and should be applied to the subfloor NOT the wood elements.

SikaBond®-5500 S should be applied to the properly prepared substrate directly from the pail and uniformly distributed by notched trowel. Press the wood floor elements firmly into the adhesive so that the underside is fully wetted. The elements can then be joined together using a hammer and an impact block. Many types of wood floors have to be tapped from the top. A distance of 10-15 mm from the wall to the wood floor must be observed in all cases.

Avoid getting adhesive on the side of the wood elements. Fresh, uncured adhesive remaining on the wood floor surface must be removed immediately with a clean cloth and if necessary cleaned with Everbuild Stick 2 Adhesives Thinner & Cleaner. Test wood floor surfaces for compatibility with Everbuild Stick 2 Adhesives Thinner & Cleaner before use.

The laying instructions of the wood floor manufacturer as well as standard construction rules must be observed.

CLEANING OF TOOLS

Clean all tools and application equipment with Everbuild Stick 2 Contact Thinner and Cleaner immediately

after use. Hardened / cured material can only be mechanically removed.

LIMITATIONS

- SikaBond®-5500 S is only suitable for experienced applicators.
- If, according to wood floor suppliers or producers deviation from the standards is permissible, temperatures between +10°C and +35°C must be observed for the adhesive.
- Wood floors in non insulated areas such as basements, or other areas without a damp proof membrane, must only be installed after the application of Sikafloor® EpoCem sealed with Sika® Primer MB to control the moisture. For detailed instructions consult the Product Data Sheets or contact our Technical Department.
- Do not use on PE, PP, TEFLON, and certain plastized synthetic materials (carry out pre-trials or contact our Technical Department).
- Some primers can negatively influence the adhesion of SikaBond®-5500 S (pre trials recommended).
- When laying bonded wood flooring, always make sure that any wood surface sealer coatings do not come into contact with the adhesive. However if direct contact with the adhesive is unavoidable, then the compatibility of the sealing coats must always be checked and confirmed before use. For further information or assistance please contact Sika Technical Department.
- Installation of magnesite or on insulating bituminous layers is not recommended.
- The product and its vapours are highly inflammable, ensure adequate air ventilation during application and curing.
- Keep away from flames and sparks and do not smoke around application area.

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

EVERBUILD BUILDING PRODUCTS LTD

Site 41, Knowsthorpe Way
Cross Green Industrial Estate
Leeds, LS9 0SW
Tel: 0113 240 3456
Web: www.everbuild.co.uk
Twitter: @everbuild

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet
SikaBond®-5500 S
April 2019, Version 01.02
020512030000000005



BUILDING TRUST



ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaBond-5500S-en-GBEVER-(04-2019)-1-2.pdf