



CP80 Clad-Seal Steel & Cladding Coating



Technical Data

Pack Size
10L

Colours
A wide range of colours

Application Tool
Brush, Roller or Spray

Suitable Substrates
Plastisol, Ferrous, non-ferrous metals

Coverage
Approximately 10m² per litre dependent on the nature and porosity of the surface

Application Temperature
8°C - 25°C

Humidity Temperature
Less than 85%



Silicone Technology



Satin Finish



Self Priming



High Water Resistance



Rust Inhibiting Technology



Chemically Resistant

DESCRIPTION

WetherTex CP80 Clad-Seal Steel & Cladding Coating is a high performance, self priming, exterior quality satin paint for use on a variety of metal substrates. Developed using advanced Optilife silicone technology, CP80 is quick drying, highly water resistant and offers excellent protection against rust for up to 12 years.

PREPARATION

Ensure all surfaces to be painted are clean, dry and free from grease and loose or flaking material that may impair adhesion. Any faults in the substrate, particularly those that can lead to moisture penetration, must be rectified or can affect the finish quality. If your substrate has been previously painted rub down with a fine waterproof abrasive paper and then rinse thoroughly. Bare substrates should also be abraded in a similar manner to allow improved adhesion. Please avoid inhaling any sanding dust and always wear a face mask if fine sanding. Special precautions should be taken during preparation of pre-1960's paint surfaces over wood and metal as they may contain harmful lead.

APPLICATION

Stir the product thoroughly and do not contaminate. For the best results apply by spray, also can be applied by brush or roller. Application tool type and quality may influence the finished appearance. Apply liberally and avoid overspreading. Not to be applied below 8°C. Recommended application 2 coats. On bare substrates please thin CP80 with 10% clean water. Under normal conditions will be dry after 1-2 hours, and can add additional coats after 3-4 hours. Ensure good ventilation during drying and application. Do not apply externally when rain or other inclement weather is imminent, ensure substrate is dry.

STORAGE

When stored unopened in a dry place at temperatures above 5°C, shelf life is 12 months from the date of manufacture. Once you have completed painting ensure you remove as much product as possible from your application tool. If you have any leftover product, ensure that you close the tin by replacing the lid firmly and securely and store in a safe place. Protect from frost. To avoid the risk of spillage, always store and transport in a secure upright position.

TOOL CLEANING

All equipment must be washed with clean, cold water after use. Waste material should not be emptied in the drainage systems. Some local authorities have special facilities for the disposal of leftover paint. Please do not add any product into drains or watercourses.

HEALTH & SAFETY INSTRUCTIONS

For further information, please request the material safety data sheet for this product by visiting www.wetherTex.co.uk

IMPORTANT INFORMATION

The environmental climatic conditions for application and drying are critical. The following conditions can negatively affect the product performance and should be avoided, and taken into full consideration in the first 24 hours after application:

- If frost or heavy rain is forecast
- Relative Humidity is above 85%
- In temperatures below 8°C or above +25°C
- If the substrate is hot (at above 30°C) or below +1°C
- Coverage rates are approximate and do not take into account wastage and uneven substrates

The product must be protected against heavy rain, direct sun or wind in the first 24 hours after application. Sheeting the façade or the scaffold is advised to protect against this. For this particular product if these parameters are not met polymer film damage, wash off, discolouration and potential failure can occur. It is the responsibility of the application contractor to manage and record the weather conditions during application and curing of the product.

To the best of our knowledge and belief, this information is true and accurate. However, as conditions of use of the product and the expertise of any labour involved are beyond our control, the end user must satisfy themselves by prior testing that the product is suitable for their specific application if no spec has been provided for the project in hand. No responsibility can be accepted, nor any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that they have consulted our latest literature.