

PRODUCT DATA SHEET

Sikafloor®-3 QuartzTop

Mineral Dry Shake Floor Hardener

PRODUCT DESCRIPTION

Sikafloor®-3 QuartzTop is a one-part, pre-blended, coloured mineral dry shake hardener for concrete comprising of cement, specially selected quartz mineral aggregates and admixtures.

USES

Sikafloor®-3 QuartzTop may only be used by experienced professionals.

Sikafloor®-3 QuartzTop provides a hard wearing, mineral dry shake topping for monolithic floors. When sprinkled and trowelled into fresh wet concrete floors, it forms a wear resistant smooth surface. Typical uses are in warehouses, factories, shopping centres, public areas, and anywhere where a durable and wear resistant floor is the key requirement.

CHARACTERISTICS / ADVANTAGES

- Medium wear resistance rating
- Provides impact resistance
- Cost effective surface hardener
- Dustproof
- Fast application
- Easy cleaning
- Increased resistance to oils and grease
- Quality assured factory blending

APPROVALS / STANDARDS

Cement based screed CT-C70-F7-AR1,0 according to EN 13813, declaration of performance 0208030400100000621180, and provided with CE marking.

Cement based screed Afl according to EN 13813, declaration of performance 0208030400100000621180, and provided with CE marking.

PRODUCT INFORMATION

Chemical Base	Natural mineral aggregates graded and mixed with cement, admixtures and pigments.
Packaging	25 kg bags
Shelf Life	12 months from date of production
Storage Conditions	Store in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C.
Appearance / Colour	Natural (concrete grey)
Density	~2250 kg/m ³ (28 days)

TECHNICAL INFORMATION

Abrasion Resistance	Class AR1.0 Note: Sikafloor®-3 QuartzTop has a BCA abrasion depth ~52 µm and ~5.5 cm ³ /50 cm ² , Böhme.	(EN 13892-4, BCA)
----------------------------	---	-------------------

SYSTEM INFORMATION

System Structure	Substrate	Fresh concrete slab (See Substrate Quality)
	Dry Shake	Manual or machine application of Sikafloor®-3 QuartzTop Levelling of surface by means of power trowel or laser screed. Final smoothing with power trowel.
	Curing Compound	Sikafloor® ProSeal or Sikafloor® ProSeal W or Sikafloor® ProSeal Pro or Sikafloor® ProSeal 90

Use products mentioned above as indicated in their respective Product Data Sheets.

APPLICATION INFORMATION

Consumption	~4–5 kg/m ² . The consumption will depend on application method and the concrete mix (w:c ratio). This figure does not allow for surface profile and wastage.	
Layer Thickness	~2.5–3.0 mm at the recommended coverage of ~ 5.0 kg/m ² .	
Ambient Air Temperature	+5 °C minimum / +30 °C maximum	
Relative Air Humidity	30 % minimum / 98 % maximum	
Substrate Temperature	+5 °C minimum / +30 °C maximum	
Applied Product Ready for Use	Substrate Temperature	Foot Traffic
	+10 °C	~18 hours
	+20 °C	~12 hours
	+30 °C	~8 hours

The above values are dependant upon the concrete reaching its design strength for serviceability and will be affected by changing ambient conditions, particularly temperature and relative humidity.

VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- The application of Sikafloor®-3 QuartzTop must not be carried out in strong wind or in dry conditions.
- Do not use concrete where some cement has been replaced by fly ash, as this makes the mix sticky and less workable.
- Variations in concrete characteristics such as water content and cement may lead to slight colour variations.
- Dry shake hardeners give a finish to concrete with some colour variation across the floor due to the natural variability of the concrete onto which they are applied.
- To ensure optimum colour consistency, it is essential that the floor laying operation is as clean, and protected from the environment as much, as possible.
- Colour variation during the drying out period is normal for this system and is to be expected.
- Every effort must be made to ensure an even application of Sikafloor®-3 QuartzTop. Correct timing and trowelling techniques are essential.
- At low relative humidity (below 40 %), efflorescence can appear on the surface.
- At high relative humidity (above 80 %), bleeding, slower curing and hardening can occur and extended finishing operations be required.

- Shrinking joints are to be created within two days. Expansion joints are reflected in the surface of the floor.
- As a consequence of repeated power trowelling, which brings tension into the surface, fine cracks may appear on the floor. This observable fact is typical for all power trowelled concrete surfaces and does not have negative impact on the floor performance.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The concrete deliveries must be of consistent quality and comply with local standards.

Concrete characteristics are specified by its class, determined in the static design and by general recommendations for concrete mix design.

Water:cement ratio must not be too low as some water is required for hydration of the Sikafloor®-3 QuartzTop

Generally recommended water:cement ratios are between 0.45 and 0.55, and must be consistent while being poured.

The compressive strength must be a minimum of 25 N/mm².

Use of Sikament® or Sika Viscocrete® superplasticisers is advised to ensure the optimum quality of concrete and where fibres are used, their optimum dispersion within the mix.

Air Entrained Concrete is not a suitable substrate for the application of dry shake hardeners.

APPLICATION

Mechanical Application - Automatic Spreader in Conjunction with a Laser Screed

Spread Sikafloor®-3 QuartzTop evenly onto the concrete immediately after screeding at 3-5 kg/m² in one application.

Manual Application

Dependent on the conditions, remove the surface bleed water or allow it to evaporate. Sprinkle Sikafloor®-3 QuartzTop onto the screeded concrete evenly in 2 stages:

- First stage: 3 kg/m²
- Second stage: 2 kg/m²

Care must be taken to apply the product without creating ripples, etc. in the concrete surface. Casting Sikafloor®-3 QuartzTop powder carelessly or further than 2 metres from point of casting will reduce the consistency of finish.

Compaction: The first application must be worked into the slab followed immediately by the application of the second stage quantity of Sikafloor®-3 QuartzTop.

Notes:

- Never add water to the surface where the dry shake has been applied.
- Sikafloor®-3 QuartzTop results in the slab surface becoming stiff more quickly than usual. Careful trimming must take place along the edges where adjoining slabs are to be poured.
- Final finishing for closing pores and removing undulations can be achieved either by hand or powered trowel.

Application Time

Application time for dry shake products is influenced by every variable which affects the placing of concrete, and can therefore vary substantially, depending on the prevailing conditions.

For mechanical application with automatic spreader and laser screed, the spreading can start almost immediately after the concrete has been levelled to allow for the hydration of the dry shake. Compaction with the trowel can start as soon as the weight of the power trowel is supported by the concrete.

For manual application, the dry shake must be spread once the concrete can be stepped on, without leaving a print deeper than 3–5 mm.

Periodical checking of the condition and development of the concrete will determine the correct time frame for each stage and sequence of application.

CURING TREATMENT

Cure and seal Sikafloor®-3 QuartzTop immediately after finishing using a curing compound, Sikafloor® ProSeal W or Sikafloor® ProSeal-22. (Refer to relevant Product Data Sheet). The sealers additionally harden the surface, decrease dust and reduce liquid absorption.

Joints: After finishing operations and completing saw cuts, clean off any residual saw lubricant / slurry without delay. Joints can be filled with Sikaflex® PRO-3 or another appropriate Sikaflex® sealant in accordance with the floor design requirements.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

MAINTENANCE

CLEANING

To maintain the appearance of the floor after application, Sikafloor®-3 QuartzTop must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques, etc., using suitable detergents and waxes.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited



Product Data Sheet
Sikafloor®-3 QuartzTop
January 2023, Version 02.01
020815010030000010

Sikafloor-3QuartzTop-en-GB-(01-2023)-2-1.pdf